


FORM PTO-1390 (REV 11-98)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	ATTORNEY'S DOCKET NUMBER DN97-038
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371			U.S. APPLICATION NO. (If known, see 37 CFR 1.5) 09/445844
INTERNATIONAL APPLICATION NO. PCT/EP98/03583	INTERNATIONAL FILING DATE 15/06/1998	PRIORITY DATE CLAIMED 19 JUNE 1997 (19.06.97)	
TITLE OF INVENTION PLASTIC COMPOSITIONS HAVING MINERAL-LIKE APPEARANCE			
APPLICANT(S) FOR DO/EO/US YANG, SHIJUN; KEATING, PAUL JOSEPH			
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:			
<ol style="list-style-type: none"> 1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1). 4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date. 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) <ol style="list-style-type: none"> a. <input checked="" type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> has been transmitted by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)). 7. <input type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) <ol style="list-style-type: none"> a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> have been transmitted by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). 			
Items 11. to 16. below concern document(s) or information included:			
<ol style="list-style-type: none"> 11. <input checked="" type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. 12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13. <input type="checkbox"/> A FIRST preliminary amendment. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 14. <input type="checkbox"/> A substitute specification. 15. <input type="checkbox"/> A change of power of attorney and/or address letter. 16. <input checked="" type="checkbox"/> Other items or information: PCT REQUEST (Form PCT/RO/101); AMENDED REQUEST; NOTIFICATION OF DECISION CONCERNING REQUEST FOR RECTIFICATION; NOTIFICATION OF RECEIPT OF RECORD COPY; NOTIFICATION CONCERNING SUBMISSION OR TRANSMITTAL OF PRIORITY DOCUMENT; INTERNATIONAL SEARCH REPORT; 1ST PAGE OF INTERNATIONAL PUBLICATION NO. WO 98/59006; NOTICE INFORMING THE APPLICANT OF THE COMMUNICATION OF THE INTERNATIONAL APPLICATION TO THE DESIGNATED OFFICES; NOTIFICATION OF RECEIPT OF DEMAND BY COMPETENT INTERNATIONAL PRELIMINARY EXAMINING AUTHORITY; INFORMATION CONCERNING ELECTED OFFICES NOTIFIED OF THEIR ELECTION; NOTIFICATION OF TRANSMITTAL OF THE INTERNATIONAL PRELIMINARY EXAMINATION REPORT; INTERNATIONAL PRELIMINARY EXAMINATION REPORT. 			

U.S. APPLICATION NO. (if known, see 37 CFR 1.53) 097445844		INTERNATIONAL APPLICATION NO. PCT/EP98/03583		ATTORNEY'S DOCKET NUMBER DN97-038			
17. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO. \$970.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$840.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$760.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$670.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) \$96.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS		PTO USE ONLY	
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$ 130.00			
CLAIMS		NUMBER FILED		NUMBER EXTRA		RATE	
Total claims		19 - 20 =				X \$18.00	
Independent claims		3 - 3 =				X \$78.00	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				+ \$260.00		\$ 260.00	
TOTAL OF ABOVE CALCULATIONS =				\$ 1230.00			
Reduction of 1/2 for filing by small entity, if applicable. A Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28).				\$			
SUBTOTAL =				\$ 1230.00			
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$			
TOTAL NATIONAL FEE =				\$ 1230.00			
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				+		\$ 80.00	
TOTAL FEES ENCLOSED =				\$ 1310.00			
				Amount to be:		\$	
				refunded		\$	
				charged		\$	
a. <input type="checkbox"/> A check in the amount of \$ _____ to cover the above fees is enclosed.							
b. <input checked="" type="checkbox"/> Please charge my Deposit Account No. <u>01-2717</u> in the amount of \$ <u>1310.00</u> to cover the above fees. A duplicate copy of this sheet is enclosed.							
c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>01-2717</u> . A duplicate copy of this sheet is enclosed.							
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.							
SEND ALL CORRESPONDENCE TO: GILBERT W. RUDMAN ELF ATOCHEM NORTH AMERICA, INC. PATENT DEPARTMENT - 26TH FLOOR 2000 MARKET STREET PHILADELPHIA, PA 19103-3222 U.S.A.							
				SIGNATURE  GILBERT W. RUDMAN NAME			
				27-589 REGISTRATION NUMBER			

PLASTIC COMPOSITIONS HAVING MINERAL-LIKE APPEARANCE

This invention relates to composite plastics
5 compositions useful in the preparation of simulated natural
substances, such as stone-like and mineral-like materials.
In particular the present invention involves the use of
specific crosslinked polymers together with certain
thermoplastic matrices to provide composite plastics
10 compositions having a mineral-like appearance, especially
an appearance similar to that of granite.

There currently exists a need for synthetic materials
that mimic the appearance of mineral-like or ceramic-like
materials, such as natural stone, and in particular
15 granite, for use in the manufacture of flooring, tiles,
counter tops, sinks, spas, sanitaryware, architectural
articles and other ornamental materials. For example,
acrylic "granite" sheet products useful in spas,
sanitaryware and outdoor applications are currently
20 prepared by cell or continuous casting processes where
small granulates are suspended in monomer or
monomer/polymer mixtures and then "cured," such as is
described in U.S. Patent No. 5,304,592 and WO 97/14749.
These thermoset materials can not be further fabricated by
25 conventional thermoplastic processing methods (such as
sheet extrusion and injection molding operations);
furthermore, the thermoset processes currently require
special handling steps or raw material limitations to
uniformly suspend the granulates in the polymerizing matrix
30 during the "cure" step. Reuse and recycling of waste and
off-grade materials, such as trimmings, from prior art
sheet materials is impractical due to the inherent

intractability of the thermoset materials. Prior art "granite" sheet products prepared by casting methods generally have poor impact strength, for example brittleness, and are limited in their adaptability to various formulation or processing methods for producing final articles. In addition, the prior art materials often provide poor adhesion to substrate surfaces resulting in subsequent "delamination" of composite articles.

It is, therefore, desirable to be able to provide thermoplastic materials that may be fabricated by conventional thermoplastic equipment (such as extrusion or injection molding) for use in spas and outdoor architectural applications; there is a need for an economical and efficient method for reuse and recycling of waste materials that is not available with current thermoset casting processes.

The problem addressed by the present invention is to overcome the deficiencies of prior methods used to prepare mineral-like plastics by providing materials that are processable by less labor intensive methods, such as coextrusion or extrusion, while also improving the economics of the processing by allowing for reuse and recycling of waste materials.

The present invention provides a composite plastics composition comprising a particulate crosslinked polymer dispersed within a thermoplastic matrix, wherein (a) the composite plastics composition comprises 10 to 45 weight percent of the crosslinked polymer, based on the weight of the composite plastics composition, and the crosslinked polymer has a particle size substantially from 0.2 to 1.2 millimeters; (b) the crosslinked polymer comprises 0.1 to 15 weight percent inert filler and 0.1 to 20 weight percent

crosslinker, based on the total weight of crosslinked polymer; and (c) the crosslinked polymer is visually differentiable from the thermoplastic matrix.

5 The present invention further provides a process for preparing a composite plastics composition comprising (a) preparing a crosslinked polymer comprising 0.1 to 15 weight percent inert filler and 0.1 to 20 weight percent crosslinker, based on the weight of crosslinked polymer; (b) comminuting the crosslinked polymer to particles having
10 a particle size substantially from 0.2 to 1.2 millimeters; (c) dispersing 10 to 45 weight percent of the particles of crosslinked polymer within 55 to 90 weight percent of a thermoplastic matrix by a heat processing treatment; and (d) recovering the composite plastics composition as a
15 particulate material.

In another aspect, the present invention provides a composite plastics composition comprising a particulate crosslinked polymer dispersed within a thermoplastic matrix, wherein (a) the composite plastics composition
20 comprises more than 20 and up to 40 weight percent of the crosslinked polymer, based on the weight of the composite plastics composition, and the particle size of the crosslinked polymer is substantially from 0.3 to 1.2 millimeters; (b) the crosslinked polymer comprises (i) from
25 95 to 99.5 weight percent (meth)acrylic monomer units selected from one or more of methyl methacrylate, ethyl acrylate and acrylic acid; (ii) from 0.5 to 5 weight percent crosslinker units selected from one or more of allyl methacrylate, ethylene glycol dimethacrylate and
30 divinylbenzene; and (iii) from 0.3 to 5 weight percent inert filler selected from one or more of titanium dioxide, iron oxide, alumina, carbon black, pigments and silica,

based on the total weight of crosslinked polymer; (c) the thermoplastic matrix comprises (i) 50 to 60 weight percent poly(alkyl (meth)acrylate) comprising a copolymer of 80 to 99 weight percent methyl methacrylate monomer units and 1 to 20 weight percent (C_1 - C_{10})alkyl acrylate monomer units, based on the weight of poly(alkyl (meth)acrylate); and (ii) 40 to 50 weight percent impact modifier comprising a multi-stage sequentially produced polymer, based on the weight of thermoplastic matrix; and (d) the crosslinked polymer is visually differentiable from the thermoplastic matrix.

In other aspects, the present invention provides a plastics composite composition prepared according to the process described above and an article of manufacture comprising an extruded sheet material resulting from extrusion of the composite plastics composition described above.

The process of the present invention is useful for preparing a range of composite plastics compositions suitable for use in forming simulated mineral-like articles. Common to each of the composite compositions is the dispersion of a particulate crosslinked polymer within a thermoplastic matrix. We have found that composite plastics compositions based on selected crosslinked polymers, having selected crosslinking levels and a selected particle size range, result in unexpectedly improved extrusion process performance and the ability to provide "granite-like" plastics articles as compared with prior art plastics using cell-casting processes.

As used herein, the term "thermoplastic" refers to polymers that are reversibly deformable (able to be softened) after being heated above their softening or glass transition temperatures and then cooled; these materials

are capable of being repeatedly melt processed in plastic manufacturing machinery such as, for example, injection molding, extrusion, blow molding, compression molding and rotational molding. As is generally accepted by those skilled in the art, thermoplastic polymers include, for example, acrylonitrile/butadiene/styrene (ABS) terpolymer, acrylonitrile/styrene/acrylate (ASA) copolymer, polycarbonate, polyester, methyl methacrylate/butadiene/styrene (MBS) copolymer, high impact polystyrene (HIPS), acrylonitrile/acrylate copolymer, acrylonitrile/methyl methacrylate copolymer, impact modified polyolefins, impact modified polyvinyl chloride (PVC) and impact modified polymethacrylates.

As used herein, the term "thermoset" refers to polymers that are irreversibly deformable after they have been prepared in an initial configuration, that is, once the polymer is formed by chemical crosslinking (usually thermally induced) it is no longer amenable to thermal processing into other physical forms. As is generally accepted by those skilled in the art, thermoset polymers are polymers that include crosslinking as part of their preparation or have been subjected to crosslinking reactions as part of a post-treatment step, for example, allyl ester polymers, epoxy resins, crosslinked acrylic polymers and crosslinked styrenic polymers produced by suspension, emulsion, continuous-cast or cell-cast polymerization methods.

As used herein, the term "thermoforming" refers to the processing of polymers into 3-dimensional molded forms from flat plastic preformed materials, such as film or sheet, under the influence of heat, pressure or vacuum or combinations thereof.

As used herein, the term "particulate material" refers to any material in the form of separate particles or divided fragments, such as, for example, pellets, beads, powders, granules and chips.

5 As used herein, the term "alkyl (meth)acrylate" refers to either the corresponding acrylate or methacrylate ester; similarly, the term "(meth)acrylic" refers to either acrylic or methacrylic acid and the corresponding derivatives, such as esters or amides. As used herein, all
10 percentages referred to will be expressed in weight percent (%), based on total weight of polymer or composition involved, unless specified otherwise. As used herein, the term "copolymer" or "copolymer material" refers to polymer compositions containing units of two or more monomers or
15 monomer types. As used herein, "extrusion blended" and "extrusion compounded" are used synonymously and refer to the intimate mixing of two materials by melt extrusion.

The composite plastics compositions of the present invention use selected crosslinked polymers in combination
20 with selected thermoplastic materials, the latter providing a thermoplastic matrix. Crosslinked polymers useful in the present invention include, for example, crosslinked vinyl polymers (prepared from monoethylenically unsaturated monomers and various multifunctional crosslinking monomers)
25 and crosslinked condensation polymers (such as polyepoxy resins and polyesters, for example, poly(butylene terephthalate) and poly(ethylene terephthalate)). Thermoset polymers represent one class of crosslinked polymers useful in the present invention.

30 Suitable monoethylenically unsaturated monomers useful in preparing particulate crosslinked polymers of the present invention include vinylaromatic monomers, ethylene

and substituted ethylene monomers.

Suitable vinylaromatic monomers include, for example, styrene and substituted styrenes, such as α -methylstyrene, vinyltoluene, ortho-, meta- and para-methylstyrene, ethylvinylbenzene, vinylnaphthalene and vinylxylenes. The vinylaromatic monomers can also include their substituted counterparts, for example, halogenated derivatives, that is, containing one or more halogen groups (such as fluorine, chlorine and bromine).

Another class of suitable monoethylenically unsaturated monomers is ethylene and substituted ethylene monomers, for example: α -olefins such as propylene, isobutylene and long chain alkyl α -olefins (such as (C₁₀-C₂₀)alkyl olefins); vinyl alcohol esters such as vinyl acetate and vinyl stearate; vinyl halides such as vinyl chloride, vinyl fluoride, vinyl bromide, vinylidene chloride, vinylidene fluoride and vinylidene bromide; vinyl nitriles such as acrylonitrile and methacrylonitrile; acrylic acid and methacrylic acid and derivatives such as corresponding amides and esters; maleic acid and derivatives such as corresponding anhydride, amides and esters; fumaric acid and derivatives such as corresponding amides and esters; itaconic and citraconic acids and derivatives such as corresponding anhydrides, amides and esters.

A preferred class of monomers useful in preparing the crosslinked polymers of the present invention are (meth)acrylic monomers, particularly (C₁-C₂₂)alkyl (meth)acrylate monomers. Examples of the alkyl (meth)acrylate monomer where the alkyl group contains from 1 to 6 carbon atoms are methyl methacrylate (MMA), methyl acrylate and ethyl acrylate (EA), propyl methacrylate,

butyl methacrylate (BMA), butyl acrylate (BA), isobutyl methacrylate (IBMA), hexyl and cyclohexyl methacrylate, cyclohexyl acrylate and combinations thereof.

5 Examples of alkyl (meth)acrylate monomers where the alkyl group contains from 7 to 22 carbon atoms are 2-ethylhexyl acrylate (EHA), 2-ethylhexyl methacrylate, octyl methacrylate, decyl methacrylate, isodecyl methacrylate (IDMA, based on branched (C₁₀)alkyl isomer mixture), undecyl methacrylate, dodecyl methacrylate (also known as
10 lauryl methacrylate), tridecyl methacrylate, tetradecyl methacrylate (also known as myristyl methacrylate), pentadecyl methacrylate and combinations thereof. Also useful are: dodecyl-pentadecyl methacrylate (DPMA), a mixture of linear and branched isomers of dodecyl,
15 tridecyl, tetradecyl and pentadecyl methacrylates; and lauryl-myristyl methacrylate (LMA), a mixture of dodecyl and tetradecyl methacrylates.

Additional (C₇-C₂₂)alkyl (meth)acrylate monomers include hexadecyl methacrylate (also known as cetyl
20 methacrylate), heptadecyl methacrylate, octadecyl methacrylate (also known as stearyl methacrylate), nonadecyl methacrylate, eicosyl methacrylate, behenyl methacrylate and combinations thereof; also useful are cetyl-eicosyl methacrylate (CEMA), a mixture of hexadecyl,
25 octadecyl, and eicosyl methacrylate; and cetyl-stearyl methacrylate (SMA), a mixture of hexadecyl and octadecyl methacrylate.

Suitable crosslinking monomers include, for example, ethylene glycol dimethacrylate, polyethylene glycol
30 diacrylate and dimethacrylate, propylene glycol dimethacrylate and diacrylate, glycidyl methacrylate, divinylbenzene, triallyl isocyanurate, N-

(hydroxymethyl)acrylamide, allyl acrylate, allyl methacrylate, N,N'-methylene diacrylamide and dimethacrylamide, triallyl citrate, trimethylolpropane triacrylate, trimethylolpropane trimethacrylate, and
5 diethyleneglycol divinyl ether. Preferred crosslinkers are allyl methacrylate, ethylene glycol dimethacrylate and divinylbenzene. The amount of crosslinking monomer is generally from 0.1 to 20%, typically from 0.5 to 10%, preferably from 0.5 to 5%, more preferably from 1 to 4% and
10 most preferably from more than 1.5% up to 3%, based on the total weight of the crosslinked polymer, that is, combined weight of monoethylenically unsaturated monomer and the crosslinking monomer.

Suitable free-radical initiators useful in the present
15 invention are any of the well known free-radical-producing compounds such as peroxy and hydroperoxy initiators, including, for example, acetyl peroxide, benzoyl peroxide, lauroyl peroxide, caproyl peroxide, cumene hydroperoxide, 1,1-di(tert-butylperoxy)-3,3,5-trimethylcyclohexane,
20 tert-butyl peroxyisobutyrate, tert-butyl peracetate, tert-butyl peroxy-pivalate (TBPV) and tert-butyl peroctoate (TBP, also known as tert-butylperoxy-2-ethylhexanoate). Also useful, for example, are azo initiators such as azodiisobutyronitrile (AIBN), azodiisobutyramide, 2,2'-azo-
25 bis(2,4-dimethylvaleronitrile), azo-bis(α -methylbutyronitrile) and dimethyl-, diethyl- or dibutyl azo-bis(methylvalerate). The initiator concentration is typically between 0.01 and 5%, preferably from 0.05 to 2% and more preferably from 0.1 to 1%, by weight based on the
30 total weight of the monomers. In addition to the initiator, one or more promoters may also be used; preferably the promoters are hydrocarbon-soluble.

Alternatively, little or no free-radical initiator may be used and the polymerization is then thermally induced by heating the monomer mixture.

5 The crosslinked polymer also contains inert filler that may be conveniently added to a cell casting syrup before starting the polymerization. Suitable inert fillers, include, for example, alumina (including hydrated forms), titanium dioxide, zinc oxide, zinc sulfide, iron oxide, barium sulfate, zirconium silicate, strontium sulfate, calcium carbonate, carbon black, powdered glass, silica, clay and talc. Preferred inert fillers include titanium dioxide, iron oxide, carbon black, silica, alumina, pigments and combinations thereof; most preferred is titanium dioxide. Conventional pigments or colorants include organic dyes (for example azo, anthraquinone, perinone, quinoline, pyrazolone, dioxazine, isoindoline, phthalocyanine, quinacridone and coumarin derivatives) and inorganic salts (cadmium, chromates, iron blue, cobalt blue and ultramarine blue). Typically, the amount of inert filler is from 0.1 to 15%, preferably from 0.2 to 10% and more preferably from 0.3 to 5%, based on the total weight of crosslinked polymer. The purpose of the inert filler is to enhance the visual differentiation between the crosslinked polymer component and the thermoplastic matrix component to provide the "mineral-like" or "granite-like" appearance of the finished composite plastics composition.

25 Optionally, the crosslinked polymer may contain conventional adjuvants, known to those skilled in the art, for various purposes, for example: dyes, pigments, antioxidants, ultraviolet stabilizers, dispersants, processing aids (such as spray drying aids, lubricants and mold-release agents), flame retardants, polymerization

rate-moderators and viscosity controlling materials. In addition, these same conventional adjuvants may be conveniently added at later stages in the production of the composite plastics composition, for example, during preparation of the thermoplastic material used as the thermoplastic matrix (described below) or during the production of the composite plastics composition itself where the crosslinked polymer and thermoplastic material are extrusion blended or compounded.

Typically, the particulate crosslinked polymers used according to the present invention are selected from the group consisting of crosslinked poly(alkyl (meth)acrylate), crosslinked poly(vinylaromatic), crosslinked polyester, crosslinked polyolefin, mixtures and corresponding copolymers thereof. Preferred crosslinked polymers are crosslinked poly(alkyl (meth)acrylates) and crosslinked polystyrene where the crosslinked polymer comprises 90 to 99.5% monomer units selected from one or more of vinylaromatic monomer and (meth)acrylic monomer and 0.5 to 10% crosslinker, based on the weight of crosslinked polymer.

The crosslinked polymer material is conveniently prepared by a cell casting process, for example. In a typical cell casting process a monomer syrup containing the monoethylenically unsaturated monomers, a crosslinking agent and a free-radical initiator is subjected to a temperature suitable for polymerization, depending on the monomers and initiators used. Preferred monoethylenically unsaturated monomers are alkyl (meth)acrylate monomers, for example, (C₁-C₄)alkyl (meth)acrylates, such as MMA (typically 80 to 99.5% and preferably from 95 to 99.5%, based on the total weight of monomers), methylacrylate or

EA (typically from zero to 20%, preferably from 1 to 8% and more preferably from 0.5 to 5%, based on the total weight of monomers), propyl methacrylate, BMA, BA, IBMA and combinations thereof. Optionally, acrylic or methacrylic acid may be included, typically from zero to 2%, based on the total weight of monomers.

After the crosslinked polymer is prepared, such as by cell cast polymerization, it is comminuted to a particulate material by known processes, for example, chipping, crushing, grinding, shredding or any granulation method; if suspension or emulsion polymerization processes are used to prepare the crosslinked polymer, conventional isolation processes used to recover the crosslinked polymer in particulate form include, for example filtration, coagulation and spray drying. The dimensions of the particulate crosslinked polymer are typically from 0.2 to about 1.2 millimeters (mm) or about 16 to 70 U.S. standard mesh. Generally, the particle size of the particulate crosslinked polymer is substantially from 0.25 to 1.2 mm (16 to 60 mesh), preferably from 0.3 to 1.2 mm (16 to 50 mesh), more preferably from 0.4 to 1.0 mm (18 to 40 mesh) and most preferably from 0.4 to 0.85 mm (20 to 40 mesh). When the particle size of the crosslinked polymer is smaller than about 70 mesh or larger than about 16 mesh, the extrusion blending of the crosslinked polymer into the thermoplastic matrix becomes problematic, for example "stranding" problems, and the desired "speckle-like" or "mineral-like" effect may not be readily attained in the final decorative or architectural article.

Thermoplastic materials useful to provide the thermoplastic matrix of the present invention include, for example, alkyl (meth)acrylate polymers and copolymers

having little or no crosslinker. The thermoplastic materials are conveniently prepared by conventional cell casting or melt extrusion processes and are typically provided in particulate form. In addition, the

5 thermoplastic materials may be prepared by conventional bulk (for example, continuous flow stirred tank reactor (CFSTR) processes), solution, suspension or emulsion polymerization techniques, in which case conventional isolation processes used to recover the polymer in

10 particulate form include, for example filtration, coagulation and spray drying. Conditions for polymerization of monomers to produce the thermoplastic material are similar to those described above for cell casting polymerization, except that little or no

15 crosslinker is involved; when melt extrusion methods are used, the thermoplastic material is conveniently isolated in a particulate form, such as pellets or granules. Suitable alkyl (meth)acrylate monomers include, for example, the (C₁-C₂₂)alkyl (meth)acrylates monomers

20 described above for the use in preparing the crosslinked polymers. Preferably the thermoplastic matrix material comprises a polymer or copolymer of methyl methacrylate (MMA); typical copolymers include 80 to 99% MMA and 1 to 20%, preferably 1 to 5%, of (C₁-C₁₀)alkyl acrylates, such as

25 methyl acrylate and ethyl acrylate (EA). A suitable commercially available poly(methyl methacrylate) type thermoplastic matrix material is Plexiglas V-grade molding powder, such as Plexiglas VO-825, VO-825HID, VO-45, VO-52 and VO-920.

30 Additional suitable thermoplastic polymers include, for example, ABS terpolymer, ASA copolymer, polycarbonate, polyester (such as poly(butylene terephthalate) and

poly(ethylene terephthalate)), MBS copolymer, HIPS,
acrylonitrile/acrylate copolymer, acrylonitrile/methyl
methacrylate copolymer, impact modified polyolefins and
impact modified PVC. More preferably the thermoplastic
5 matrix material is an impact modified polymethacrylate.

The thermoplastic matrix may be based entirely on the
aforementioned thermoplastic polymers or the thermoplastic
matrix may optionally contain modifier additives, such as
impact modifiers, in addition to the aforementioned
10 thermoplastic polymers. In general, the thermoplastic
matrix comprises 50 to 100% poly(alkyl (meth)acrylate) and
zero to 50% impact modifier, based on the weight of
thermoplastic matrix. Typically, the thermoplastic matrix
contains 25 to 100%, preferably 30 to 70%, more preferably
15 45 to 60% and most preferably 50 to 60%, thermoplastic
polymer, such as poly(alkyl (meth)acrylate); and zero to
75%, preferably 30 to 70%, more preferably 40 to 55% and
most preferably 40 to 50%, impact modifier, based on the
total weight of thermoplastic matrix. Suitable impact
20 modifiers include, for example, elastomeric polymers such
as graft polymers of methyl methacrylate and styrene on
butadiene (MBS), graft polymers of acrylonitrile and
styrene on butadiene (ABS), copolymers of styrene and
butadiene, poly(butyl acrylate) and poly(2-ethylhexyl
25 acrylate) and copolymers thereof, copolymers of butyl
acrylate and methyl acrylate, terpolymers of butyl
acrylate/styrene/methyl methacrylate, chlorinated
polyethylene, acrylate block polymers, styrene block
polymers, ethylene/propylene/diene copolymer (EPDM),
30 ethylene/vinyl acetate copolymers,
acrylonitrile/styrene/acrylic ester terpolymers, styrene-
maleic anhydride copolymers and core-shell multi-stage

sequentially-produced polymers. Preferred impact modifiers include MBS polymers, core-shell multi-stage sequentially-produced polymers, and styrene and acrylate block polymers.

Typical core-shell multi-stage polymers useful as
5 impact modifiers for thermoplastic polymers include, for example, those disclosed in U.S. Patent No. 3,793,402. The multi-stage sequentially-produced polymers are characterized by having at least three stages in a sequence of a non-elastomeric first stage, an elastomeric second
10 stage and a non-elastomeric third stage. Preferably the first stage polymer has a glass transition temperature (T_g) greater than about 25°C, preferably greater than about 60°C, and is a polymer comprising (a) 70 to 100%, preferably 85 to 99.9%, monomer units of one or more of
15 (C₁-C₄)alkyl (meth)acrylates (preferably MMA and EA), styrene, substituted styrene, acrylonitrile and methacrylonitrile, based on the weight of the first stage polymer; (b) zero to 10%, preferably 0.05 to 5% and more preferably 0.5 to 2%, monomer units of a copolymerizable
20 polyfunctional crosslinking monomer; (c) zero to 10%, preferably 0.05 to 5%, monomer units of a copolymerizable graftlinking monomer, such as the allyl, methallyl and crotyl esters of monoethylenically unsaturated monocarboxylic and dicarboxylic acids, for example allyl
25 methacrylate; and (d) zero to 30%, preferably 0.1 to 15%, of other copolymerizable monoethylenically unsaturated monomers.

The second stage polymer is prepared in the presence of the first stage polymer and preferably has a T_g of less
30 than about 25°C, preferably less than about 10°C, if it were to be prepared alone, that is in the absence of the presence of the first stage polymer. Typically the second

stage polymer comprises (a) 50 to 99.9%, preferably 70 to 99.5%, monomer units of one or more of (C₁-C₈)alkyl (meth)acrylates, (preferably (C₁-C₄)alkyl acrylates, particularly BA), butadiene and substituted butadienes (such as isoprene, chloroprene and 2,3-dimethylbutadiene), based on the weight of the second stage polymer; (b) zero to 49.9%, preferably 0.5 to 30%, monomer units of a copolymerizable monoethylenically unsaturated monomer, such as styrene and substituted styrene; (c) zero to 5% monomer units of a copolymerizable polyfunctional crosslinking monomer, such as ethylene glycol diacrylate and divinylbenzene; and (d) 0.05 to 5% monomer units of a copolymerizable graftlinking monomer, such as those described above.

The third stage polymer is prepared in the presence of the product of the first and second stage polymers and preferably has a T_g greater than about 25°C, preferably greater than about 50°C, if it were to be prepared alone, that is in the absence of the presence of the product of the first and second stage polymers. Typically the third stage polymer comprises (a) 70 to 100%, preferably 85 to 99.9%, monomer units of one or more of (C₁-C₄)alkyl (meth)acrylates, styrene, substituted styrene, acrylonitrile and methacrylonitrile, based on weight of the second stage polymer; (b) zero to 30, preferably 0.1 to 15%, monomer units of a copolymerizable monoethylenically unsaturated monomer; (c) zero to 10%, preferably 0.05 to 5%, monomer units of a copolymerizable polyfunctional crosslinking monomer; and (d) zero to 5% monomer units of a copolymerizable graftlinking monomer, such as those described above.

Typically the multi-stage polymer comprises at least

three stages in a sequence of 10 to 40%, preferably 20 to 40%, of the first stage; 20 to 60%, preferably 30 to 50%, of the second stage; and 10 to 70%, preferably 20 to 50%, of the third stage, based on the total weight of the multi-stage polymer.

Other copolymerizable mononethylenically unsaturated monomers referred to above include alkyl (meth)acrylates, alkoxy (meth)acrylates, hydroxyalkyl (meth)acrylates, cyanoethyl (meth)acrylates, (meth)acrylamides, (meth)acrylic acids and vinylaromatics, for example.

Typical copolymerizable polyfunctional crosslinking monomers include, for example, ethylene glycol dimethacrylate and diacrylate, 1,3-butylene glycol dimethacrylate and diacrylate, 1,4-butylene glycol dimethacrylate and diacrylate, propylene glycol dimethacrylate, divinylbenzene, trimethylolpropane triacrylate, trimethylolpropane trimethacrylate and diethyleneglycol divinyl ether. Preferred crosslinkers are ethylene glycol dimethacrylate and divinylbenzene. For the purpose of the preparing the multi-stage sequentially-produced polymers, the crosslinkers are selected from polyfunctional monomers where the crosslinking groups have similar reactivities, such as those just described. Polyfunctional "crosslinking" monomers where the functional groups have different reactivities, such as allyl methacrylate and methallyl and crotyl esters of monoethylenically unsaturated monocarboxylic and dicarboxylic acids, are referred to as "graftlinking" monomers when used in preparation of the multi-stage sequentially-produced polymers described herein; however they are considered to be among the general group of "crosslinking" monomers useful in the preparation of other

crosslinked polymers, such as those used to provide the particulate crosslinked polymers of the present invention.

Preferably, the multi-stage polymer is an emulsion polymer comprising monomer units of methyl methacrylate in the first stage, monomer units selected from one or more of butadiene, styrene and (C₁-C₈)alkyl acrylates in the second stage, and monomer units selected from one or more of (C₁-C₄)alkyl methacrylates, styrene and acrylonitrile in the third stage.

10 The multi-stage polymers may be prepared by a number of well-known techniques, for example, by emulsion polymerization, where a subsequent stage monomer mixture is polymerized in the presence of a previously formed product. For example, "sequentially produced" or "sequentially
15 polymerized" refer to polymers prepared in aqueous dispersion or emulsion form where successive monomer charges are polymerized onto or in the presence of a preformed latex prepared by the polymerization of a prior monomer charge and stage.

20 The blend of the multi-stage polymer (as an impact modifier) with the thermoplastic polymer can be accomplished by any known method, such as dispersing the multi-stage polymer in a monomer mixture used to prepare the thermoplastic polymer or in a monomer-polymer syrup
25 mixture which together would provide the desired thermoplastic polymer. Alternatively, the multi-stage polymer can placed in a casting mix in the form of an emulsion, suspension or dispersion in water or in an organic carrier; the water or organic carrier can then be
30 removed before or after casting into the final thermoplastic polymer form. The multi-stage polymer may also be blended with the thermoplastic polymer by extrusion

compounding. Additional specific methods and details of blending the thermoplastic polymer and impact modifiers are disclosed in U.S. Patent No. 3,793,402.

A preferred thermoplastic matrix material is impact modified poly(methyl methacrylate) commercially available as Plexiglas DR101, MI-5 and MI-7 molding powder. Plexiglas (North and South America, Orogas in Europe and Asia) is a trademark of Rohm and Haas Company, Philadelphia, PA, USA.

In one embodiment of the present invention, the composite plastics compositions of the present invention are prepared by compounding or blending the crosslinked polymer with the thermoplastic material by dispersing particles of crosslinked polymer within a matrix of thermoplastic material using a suitable heat processing treatment. Suitable heat processing treatments include, for example, extrusion blending, hot-melt kneading and hot-melt batch mixing. For example, the crosslinked polymer particles may be melt processed by hot melt extrusion blending or compounding with thermoplastic particles and the resultant composite plastic composition is recovered in particulate form, such as pellets. Hot-melt batch mixing may include dispersion of the crosslinked particles into a melt of the thermoplastic matrix in a conventional batch mode, such as a stirred kettle; alternatively, the thermoplastic may be heated and mixed with a carrier solvent, such as toluene, and then batch mixed with the crosslinked particles, followed by flash evaporation of the solvent; the resultant composite plastic composition can then be granulated by conventional means. The resultant pellets are typically translucent to clear granules containing distinct "speckle-like" particles, the latter

being representative of the crosslinked polymer used in the compounding process.

Typically 10 to 45%, preferably 15 to 40% and more preferably greater than 20 to 40%, crosslinked polymer particles are combined with 55 to 90%, preferably from 60 to 85% and more preferably from 60 to less than 80%, thermoplastic particles, based on the combined weight of crosslinked polymer and thermoplastic particles. The extrusion blending process allows for a relatively uniform distribution of the thermoset material throughout the thermoplastic matrix without requiring similar densities of the two materials, as is typically required in conventional casting processes used in the prior art. Preferably a low-shear screw design is used to minimize processing problems, such as residual monomer odor, vent plugging, flowability problems and stranding problems.

Extrusion temperatures are typically in the range of 220° to 260°C and the extruder screw design should provide low shear to prevent the loss of the distinct granite-like appearance and to maintain particle integrity. The cooling bath temperature (strand takeup) is typically maintained at about 60° to 70°C and the vent section of the extruder may be vacuumed to minimize pelletization problems.

During the extrusion blending process, control of the particle size of crosslinked polymer is important for optimum processing and ultimate "granite-like" appearance of the finished articles. When the particles are very large, that is, greater than about 1.2 mm or 16 mesh, "stranding" problems may develop during sheet extrusion or extrusion blending processes. When the particles are much smaller than about 0.2 mm or 70 mesh, the extruder die may plug frequently and stranding problems may develop; in

addition, poor "granite-like" appearance occurs.

5 If the crosslinking level is too low, that is, below about 0.5%, the crosslinked polymer particles may "smear" into thermoplastic matrix material after multiple passes during extrusion, resulting in blurred or non-differentiated mineral-like appearance. If the crosslinking level is too high, that is, above about 10%, the yield of desired particle size during the comminution step is reduced due to generation of fine particles smaller than about 0.2 mm (70 mesh) and the sheet surfaces of the final article may be rough and require a secondary treatment such as press polishing. Preferably, the crosslinker level is from 0.5 to 5% and more preferably from 1 to 4%.

15 An example of the importance of the degree of crosslinking in the particulate material regarding the maintenance of particle integrity during processing can be seen in the multiple extrusion processes typically involved in preparing monolithic and multilayered composite sheets. When prior art particles ("C" particles from Safas Corp., mixture of thermoplastic and thermoset material - see Example 3E-3G) were extrusion blended with thermoplastic matrix material at a low concentration (less than 10%), the final sheet provided a hazy speckle-like appearance (not "granite-like"). At a 25% use rate, about half of the "C" particles were smeared into thermoplastic matrix resulting in a non-differentiated final product appearance. When the use rate of "C" particles was above 30%, extrusion process problems were observed (power surges, poor flow, stranding problem, extruder pluggage) as well as complete loss of granite-like effect in the composite plastic material. Composite plastic compositions prepared using the "C"

particles discussed above (thermoset/thermoplastic particles disclosed in U.S. Patent No 5,304,592) undergo loss of granite-like appearance under the extrusion processing conditions described in Example 3, apparently
5 due to insufficient particle integrity.

Simulated mineral articles are prepared from the composite plastics compositions of the present invention by heat treatment into a physical form selected from the group consisting of sheet, laminated sheet and molded material.
10 Suitable heat treatment processes include, for example, melt extrusion, coextrusion, blow molding, sheet forming and thermoforming.

The composite plastics compositions of the present invention can be extruded into monolithic sheet for indoor
15 or outdoor applications, or coextruded with other high-impact grade thermoplastics such as ABS terpolymer, ASA copolymer, polycarbonate, MBS copolymer, HIPS, acrylonitrile/acrylate copolymer, acrylonitrile/methyl methacrylate copolymer, impact modified polyolefins and
20 impact modified PVC, to produce a multilayer composite sheet useful for spa, sanitary ware, countertops, bathroom and kitchen fixtures, wall decorations and other thermoforming applications. The composite plastics compositions may also be injection molded into different
25 forms for other applications such as facets, frames, door handles, window frames, sinks, shower stalls, building panels, plumbing fixtures, tiles, refrigerator walls, floor coverings and decorative moldings.

The invention is further illustrated by way of example
30 in the following Examples. All ratios, parts and percentages are expressed by weight unless otherwise specified, and all reagents used are of good commercial

quality unless otherwise specified. Abbreviations used in the Examples and Tables are listed below with the corresponding descriptions.

5	MMA	=	Methyl Methacrylate
	EA	=	Ethyl Acrylate
	AA	=	Acrylic Acid
	ALMA	=	Allyl Methacrylate
	AIBN	=	Azodiisobutyronitrile
10	TBP	=	tert-Butyl Peroctoate
	TBPV	=	tert-Butyl Peroxypivalate
	TiO ₂	=	Titanium Dioxide

Example 1 Preparation of Crosslinked Polymer

15 A monomer mixture was prepared by combining
crosslinker monomer (ALMA), alkyl (meth)acrylate monomer
(MMA), (meth)acrylic comonomer (EA, AA), inert filler
(TiO₂, silica, carbon black), free-radical initiator (AIBN,
TBP, TBPV mixture, 0.05%) polymerization rate-moderator
20 (terpinolene, 0.01%) and lubricant (2% stearic acid). All
% values are by weight based on total weight of monomers.

 The ingredients listed above (monomer mixture) were
mixed in a glass casting cell or polyvinyl alcohol (PVA)
casting bag and then subjected to a controlled temperature
25 of 60°C for 14 hours, followed by a post-cure (heating at
130°C for 2 hours). The finished crosslinked polymer was
recovered by disassembly of the cell or removal of the PVA
bag and was then granulated into particulate form using any
conventional grinding method, for example, crushing,
30 attrition mill or Cumberland cutter. The granulated
crosslinked polymer was then screened to a desired particle
size distribution.

 Table I summarizes crosslinked polymers (component %
based on weight of crosslinked polymer, monomers plus

crosslinker) evaluated in the composite plastic compositions of the present invention. Crosslinked polymers typically contained less than 1% residual monomer and were screened after comminution to particulate form, with a typical isolated yield of 65 to 80% particles of 0.4 mm to 1mm (-18+40 U.S. standard mesh).

Table I
Compositions of Crosslinked Polymers

ID	Monomers ^a	Crosslinker ^b	Inert Filler ^c
1A	94.5/3.1/2.1	0.3	3
1B	93.0/3.0/2.0	2.0	3
1C	93.0/3.1/0.0	3.9	3
1D	95.0/3.1/0.0	1.9	2/2 ^d
1E ^e	96/4/0	0.0	2.6

a = MMA/EA/AA

b = ALMA

c = Titanium Dioxide

d = Silica/Carbon Black

e = Uncrosslinked, weight average molecular weight approx 3×10^6

Example 2 Preparation of Thermoplastic Matrix Material

The thermoplastic matrix material used in evaluating the composite plastic compositions of the present invention was impact modified poly(methyl methacrylate) commercially available as Plexiglas DR101 molding powder from Rohm and Haas Co, Philadelphia, PA, USA.

Example 3 Preparation of Composite Plastic Composition

The particulate crosslinked polymer (0.4 to 1 mm granules) of Example 1 were extrusion blended (using a single- or twin-screw extruder at 220 to 260°C) with the

thermoplastic material (pellets of approximately 3 to 6 mm
in diameter and length) of Example 2 (in the relative
amounts indicated) into the composite plastic composition
of the present invention (see Table 2). The pelletized
5 composite plastic compositions were then sheet extruded and
evaluated for their aesthetic and processing
characteristics. Examples 3A-3D represent the present
invention and 3E-3G represent comparative examples that
replace the particulate crosslinked polymer of the present
10 invention with thermoplastic/thermoset particles based on
U.S. Patent No. 5,304,592 (provided by Safas Corp.).

15

20

25

30

Table 2

ID	Crosslinked Polymer	Thermoplastic Material	Sheet Extrusion	Sheet Appearance
3A	Ex 1A (35%)	Ex 2 (65%)	Crosslinked particles melted into matrix	No granite texture
3B	Ex 1B (35%)	Ex 2 (65%)	Good processing	Granite texture and smooth surface
3C	Ex 1C (35%)	Ex 2 (65%)	Poor process, stranding and pelletizing problems	Rough surface
3 F **	"C" Particles ^a (25%)	Ex 2 (75%)	Majority of particles melted into matrix	Poor granite texture and poor particle/matrix differentiation*
3 G **	"C" Particles ^a (32%)	Ex 2 (68%)	Poor process, stranding and pelletizing problems	No granite texture, opaque*
3H	Ex 1B/1D (< 10%)	Ex 2 (>90%)	Good processing	Transparent, little or no granite texture
3J	Ex 1B/1D (>45%)	Ex 2 (<55%)	Poor process, stranding and pelletizing problems	Rough surface
3K	Ex 1E (25-35%)	Ex 2 (65-75%)	Good processing	No granite texture

* = appearance from Carver press "button"

** = comparative composite plastic composition, not of the present invention

^a = thermoplastic/thermoset particles from Safas Corp., -25+35 ANN

Example 4 Physical Properties of Composite Plastics
Compositions

Composite plastics compositions based on different crosslinked polymers (prepared according to Example 1) and the thermoplastic matrix material of Example 2 were fabricated into test samples of sheet (injection molding and sheet extrusion) or film (Carver press) and evaluated for overall appearance and impact strength.

The Falling Dart [dart: 1.36 kilogram (3-pound), 0.63 centimeter, cm (0.25 inch, in) radius; sample of 15.2 cm (6 in) x 15.2 cm (6 in) x 0.32 cm (0.125 in)] and Notched Izod (23°C, 73°F) tests were conducted according to ASTM method D256 (published by the American Society for Testing and Materials) as measures of impact strength.

Table 3

Composite Plastics Composition	Falling Dart Impact Test Total energy, joules (foot-pounds)	Notched Izod joule/centimeter (foot- pound/inch)
Ex 1B/1D (15%)/Ex 2 (85%)	10.4 (7.7)	0.42 (0.79)
Ex 1B/1D (30-37%)/Ex 2 (63-70%)	3.9 (2.9)	0.29-0.30 (0.54- 0.56)

In addition to the sheet extrusion process used to evaluate the "granite-like" effect, the appearance of the compounded composite material was also visually examined using a "button" prepared on a Carver press according to the following conditions: 65 grams of composite plastic

composition pellets were placed in an "X" configuration in
a 12.7 cm x 12.7 cm x 0.25 cm thick (5 in x 5 in x 0.1 in
thick) aluminum mold between chrome-plated plates; the
press was subjected to 1 minute preheat at 188°C (370°F)
5 under 3.45×10^6 pascals (Pa) pressure (500 pounds per
square inch/psig), 1 minute heat at 188°C (370°F) under
 8.27×10^7 Pa (12,000 psig) and 1 minute cool at 10°C
(50°F) under 8.27×10^7 Pa (12,000 psig). The appearances
of the Carver press "buttons" for composite plastic
10 compositions of the present invention and that of the prior
art were consistent with those described in Table 3 for
Examples 3D and 3G, respectively.

09445844 124599

CLAIMS

1. A composite plastics composition comprising a particulate crosslinked polymer dispersed within a thermoplastic matrix, wherein:

(a) the composite plastics composition comprises 10 to 45 weight percent of the crosslinked polymer, based on the weight of the composite plastics composition, and the crosslinked polymer has a particle size substantially from 0.2 to 1.2 millimeters;

(b) the crosslinked polymer comprises 0.1 to 15 weight percent inert filler and 0.1 to 20 weight percent crosslinker, based on the total weight of crosslinked polymer; and

(c) the crosslinked polymer is visually differentiable from the thermoplastic matrix.

2. A composite plastics composition according to claim 1 wherein the thermoplastic matrix comprises 50 to 100 weight percent poly(alkyl (meth)acrylate) and zero to 50 weight percent impact modifier, based on the weight of thermoplastic matrix.

3. A composite plastics composition according to claim 2 wherein the poly(alkyl (meth)acrylate) comprises a copolymer of 80 to 99 weight percent methyl methacrylate monomer units and 1 to 20 weight percent (C₁-C₁₀)alkyl acrylate monomer units, based on total weight of the poly(alkyl (meth)acrylate).

4. A composite plastics composition according to claim 2 or 3 wherein the impact modifier is a multi-stage

sequentially-produced polymer comprising at least three stages in a sequence of a non-elastomeric first stage, an elastomeric second stage and a non-elastomeric third stage.

5 5. A composite plastics composition according to claim 4
wherein the multi-stage polymer is an emulsion polymer
comprising monomer units of methyl methacrylate in the
first stage, monomer units selected from one or more of
10 butadiene, styrene and (C₁-C₈)alkyl acrylates in the second
stage, and monomer units selected from one or more of
(C₁-C₄)alkyl methacrylates, styrene and acrylonitrile in
the third stage.

15 6. A composite plastics composition according to any one
of the preceding claims wherein the crosslinked polymer
comprises 90 to 99.5 weight percent monomer units selected
from one or more of vinylaromatic monomer and (meth)acrylic
monomer and 0.5 to 10 weight percent crosslinker, based on
the weight of crosslinked polymer.

20 7. A composite plastics composition according to claim 6
wherein the (meth)acrylic monomer is selected from one or
more of methyl methacrylate, methyl acrylate, ethyl
acrylate, acrylic acid and butyl methacrylate.

25 8. A composite plastics composition according to any one
of the preceding claims wherein the crosslinker is selected
from one or more of allyl methacrylate, ethylene glycol
dimethacrylate and divinylbenzene.

30 9. A composite plastics composition according to any one
of the preceding claims wherein the inert filler is

selected from one or more of titanium dioxide, iron oxide, alumina, pigments, carbon black and silica.

10. A composite plastics composition according to any one
5 of the preceding claims wherein the particle size of the crosslinked polymer is substantially from 0.3 to 1.2 millimeters.

11. A composite plastics composition comprising a
10 particulate crosslinked polymer dispersed within a thermoplastic matrix, wherein:

15 (a) the composite plastics composition comprises more than 20 and up to 40 weight percent of the crosslinked polymer, based on the weight of the composite plastics composition, and the particle size of the crosslinked polymer is substantially from 0.3 to 1.2 millimeters;

20 (b) the crosslinked polymer comprises (i) from 95 to 99.5 weight percent (meth)acrylic monomer units selected from one or more of methyl methacrylate, ethyl acrylate and acrylic acid; (ii) from 0.5 to 5 weight percent crosslinker units selected from one or more of allyl methacrylate, ethylene glycol dimethacrylate and divinylbenzene; and (iii) from 0.3
25 to 5 weight percent inert filler selected from one or more of titanium dioxide, iron oxide, alumina, carbon black and silica, based on the total weight of crosslinked polymer;

30 (c) the thermoplastic matrix comprises (i) 50 to 60 weight percent poly(alkyl (meth)acrylate) comprising a copolymer of 80 to 99 weight percent methyl methacrylate monomer units and 1 to 20 weight percent

(C₁-C₁₀)alkyl acrylate monomer units, based on the weight of poly(alkyl (meth)acrylate); and (ii) 40 to 50 weight percent impact modifier comprising a multi-stage sequentially produced polymer, based on the weight of thermoplastic matrix; and
(d) the crosslinked polymer is visually differentiable from the thermoplastic matrix.

12. A process for preparing a composite plastics composition comprising:
- (a) preparing a crosslinked polymer comprising 0.1 to 15 weight percent inert filler and 0.1 to 20 weight percent crosslinker, based on the weight of crosslinked polymer;
 - (b) comminuting the crosslinked polymer to particles having a particle size substantially from 0.2 to 1.2 millimeters;
 - (c) dispersing 10 to 45 weight percent of the particles of crosslinked polymer within 55 to 90 weight percent of a thermoplastic matrix by a heat processing treatment; and
 - (d) recovering the composite plastics composition as a particulate material.

13. A process according to claim 12 wherein the particles of step (b) have a particle size substantially from 0.3 to 1.2 millimeters.

14. A process according to claim 12 or 13 wherein the heat processing treatment of step (c) is selected from one or more of extrusion blending, hot-melt kneading and hot-melt batch mixing.

15. A composite plastics composition prepared by the process claimed in any one of claims 12 to 14.

5 16. A process for preparing a simulated mineral article comprising forming, with heat treatment of a composite plastics composition as claimed in any one of claims 1 to 11 into a sheet, laminated sheet or molded material.

10 17. A process according to claim 16 wherein the heat treatment is selected from the group consisting of melt extrusion, coextrusion, blow molding, sheet forming and thermoforming.

15 18. An extruded sheet material resulting from extrusion of a composite plastics composition as claimed in any one of claims 1 to 11.

20 19. A thermoformed product of a composite plastics composition as claimed in any one of claims 1 to 11.

ABSTRACT

PLASTIC COMPOSITIONS HAVING MINERAL-LIKE APPEARANCE

5

Composite plastics compositions based on the dispersion of selected crosslinked polymers in certain thermoplastic matrices are disclosed. The composite compositions are readily formed and processed by thermal extrusion processes versus conventional casting processes. Preferred composite plastics compositions based on crosslinked poly(alkyl (meth)acrylate) polymers and modified poly(alkyl (meth)acrylate) thermoplastics are especially useful in the preparation of synthetic architectural materials having a mineral-like appearance, such as that of granite.

10

15

Please type a plus sign (+) inside this box → ☐

PTO/SB/01 (12-97)

Approved for use through 9/30/00. OMB 0651-0032

Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63) <input checked="" type="checkbox"/> Declaration Submitted with Initial Filing OR <input type="checkbox"/> Declaration Submitted after Initial Filing (surcharge (37 CFR 1.16 (e)) required)	Attorney Docket Number	DN97-038
	First Named Inventor	YANG, SHIJUN
	COMPLETE IF KNOWN	
	Application Number	/
	Filing Date	
	Group Art Unit	
	Examiner Name	

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

PLASTIC COMPOSITIONS HAVING MINERAL-LIKE APPEARANCE

the specification of which
☒ is attached hereto
 OR
☒ was filed on (MM/DD/YYYY) 06/15/1998 as United States Application Number or PCT International Application Number EP98/03583 and was amended on (MM/DD/YYYY) (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

I hereby claim the benefit under 35 U.S.C. 119(e) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)	
60/050,213	06/19/1997	<input type="checkbox"/> Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

[Page 1 of 2]

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

(July 1998)

Please type a plus sign (+) inside this box →

PTO/SB/01 (12-97)
Approved for use through 9/30/00. OMB 0651-0032

Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION — Utility or Design Patent Application

I hereby claim the benefit under 35 U.S.C. 120 of any United States application(s), or 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application or PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)
60/050,213 PCT/EP98/03583	06/19/1997 06/15/1998	

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

☐ Customer Number

OR

☒ Registered practitioner(s) name/registration number listed belowPlace Customer
Number Bar Code
Label here

Name	Registration Number	Name	Registration Number
Gilbert W. Rudman	27,589	Nicholas J. DeBenedictis	25,670
Stanley A. Marcus	24,425	Royal E. Bright	26,845
William D. Mitchell	20,977		

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet PTO/SB/02C attached hereto.Direct all correspondence to: ☐ Customer Number or Bar Code Label OR ☒ Correspondence address below

Name	Gilbert W. Rudman				
Address	ELF ATOCHEM NORTH AMERICA, INC.				
Address	2000 Market Street				
City	Philadelphia	State	PA	ZIP	19103-3222
Country	US	Telephone	215/419-7636	Fax	215/419-7075

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle [if any])		Family Name or Surname	
Shijun		Yang	
Inventor's Signature	Shijun Yang PA		Date
Residence: City	Maple Glen	State	PA
		Country	US
Post Office Address	1803 Perrin Court		
Post Office Address			
City	Maple Glen	State	PA
		ZIP	19002
		Country	US

☒ Additional Inventors are being named on the 1 supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto

Please type a plus sign (+) inside this box → ☐PTO/SB/02A (3-97)
Approved for use through 9/30/98. OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

+

DECLARATION

ADDITIONAL INVENTOR(S)
Supplemental Sheet
Page ___ of ___

Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name (first and middle [if any])				Family Name or Surname			
Paul Joseph				Keating			
Inventor's Signature	<i>Paul Joseph Keating</i>				Date	12-11-99	
Residence: City	Newportville	State	PA	Country	US	Citizenship	US
Post Office Address	2727 Avenue "A"						
Post Office Address							
City	Newportville	State	PA	ZIP	19056	Country	US
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name (first and middle [if any])				Family Name or Surname			
Inventor's Signature					Date		
Residence: City		State		Country		Citizenship	
Post Office Address							
Post Office Address							
City		State		ZIP		Country	
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name (first and middle [if any])				Family Name or Surname			
Inventor's Signature					Date		
Residence: City		State		Country		Citizenship	
Post Office Address							
Post Office Address							
City		State		ZIP		Country	

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

514 Rec'd PCT/PTO

13 DEC 1999

Please type a plus sign (+) inside this box →

PTO/SB/02B (3-97)

Approved for use through 9/30/98. OMB 0651-0032

Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
are required to respond to a collection of information unless it contains a

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION — Supplemental Priority Data Sheet

Additional foreign applications:

[illegible]

Additional provisional applications:

Application Number	Filing Date (MM/DD/YYYY)

Additional U.S. applications:

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. **DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.**